

TECHNICAL DATA SHEET (TDS)

技术数据 (TDS)

Product Name(产品名称): C.I.(染料索引号): Solvent Yellow 160:1

Melting Point 熔点(°C):	157 °C	Starting Temperature of Sublimation 升华点(°C)	226°C
Bulking Value 堆比重 (ml / g)	5.6	Physical Estate 物态	Solid Powder 固体粉末
Solubility in Water 水溶性	Insoluble in Water 不溶于水	Odour 汽味	Inodorous 无汽味
Resistance to Chemical (1 g / 20 ml / 24 hr)	耐化学性 5: Excelient; 1:Poor	5 % HCL	5
		5 % NaOH	5
ABS	Heat Stability 热稳定性	°C / min	
	Light Fastness 耐光性 8: Excelient; 1:Poor	Full Shade 饱和色	
		Tint Shade 浅色	
	Contract Bleed 迁移性	(5: Excelient; 1:Poor)	
GP-PS	Heat Stability 热稳定性	°C / min	
	Light Fastness 耐光性 8: Excelient; 1:Poor	Full Shade 饱和色	280 °C / 10 min
		Tint Shade 浅色	6
	Contract Bleed 迁移性	(5: Excelient; 1:Poor)	
PMMA	Heat Stability 热稳定性	°C / min	
	Light Fastness 耐光性 8: Excelient; 1:Poor	Full Shade 饱和色	250 °C / 10 min
		Tint Shade 浅色	5
	Contract Bleed 迁移性	(5: Excelient; 1:Poor)	
HI-PS	Heat Stability 热稳定性	°C / min	
	Light Fastness 耐光性 8: Excelient; 1:Poor	Full Shade 饱和色	280 °C / 10 min
		Tint Shade 浅色	6
	Contract Bleed 迁移性	(5: Excelient; 1:Poor)	
Solubility 溶解性 g / ml	Toluene 甲苯	4.70	Pigmental Bleed 颜色 泳移性
	Ethyl Alcohol 乙醇	0.25	
	Ethyl Acetate 乙酸	0.02	
	Acetone 丙酮	1.12	
	M.E.K. 丁酮	2.20	
	MMA Monomer	0.03	
Toxicity 毒性	Acute Oral Toxicity 急性口服毒性 (LD50) Tested in Rat 大鼠试验		> 10000 mg /kg
	Skin Tolerance 皮肤适应性 Tested on Rabbits 家兔试验		微刺激
	Mucous Membrane Tolerance 粘膜适应性 Rabbits Eye 家兔眼睛试验		微刺激
Extinguishing Media 灭火介质		Foam 泡沫	Dry Powder 干粉
CO ₂ 二氧化碳			
<p>Solvent Yellow 16 is a kind of innocuity solid powder, apyrous, inexplusive. It is packed in cardboard drum or iton drum,inner linde with double plastic bags. It can't burnt or explode when it is during storage or transportation. It will be carefully used. In order to avoid powder pollution, workers should wear appliances for labour protection, such as gloves, gas defence masks etc. 透明黄 GC 是一种无毒无害、不易燃烧、不爆炸的固体粉末, 它由内衬两层塑料袋的纸板桶或铁桶包装。在储存和运输过程中不会引起燃烧或爆炸。在使用过程中, 建议操作工人佩戴手套、防尘等劳保用品。</p>			